



Allstate Sheet Rubber Flooring

www.allstaterubber.com sales@allstaterubber.com

Characteristics	Standard	Result
Hardness	ASTM D2240	Shore A 85 ± 5
Tensile Strength	ASTM D412	89 kgf / cm ²
Elongation	ASTM D412	> 300 %
Tear strength	ASTM D624	41 kgf /cm
Abrasion test	CNS 734 Akron, 1000g*15 ⁰ *1000rev	0.5 ml
Water Absorption	ASTM D570 Distilled water, room temp. 24 hrs	<1%
Dimensional stability	ASTM D2047 80 C, 6 hrs	Vertical -0.2% Horizontal -0.2%
Static coefficient of friction	ASTM D2047	0.85
Fire Behavior	ASTM E648	Class 1
Smoke Density	ASTM E662	< 450
Color fastness to light	CNS 8907	Grade 4
Electronic Resistance	ASTM D257	6.3 x 10 ¹¹ Ω-cm
Isolation Acoustic	ISO 717-2	ΔLw= 15dB
Halogens or PVC	Ultimate analysis	None
Roll Size:	4.00' x 49.2'	196.80 sf per roll

All terms & specifications are subject to change without notice.

4.11jc