



ALLSTATE RUBBER CORP.

ALLSTATE RESILIENT FLOORING, SINCE 1958

Ozone Park NYC 11416

1 718 526 7890 Fax: 1 718 849 1162

www.allstaterubber.com allstaterubber@yahoo.com

MVT/MOSAIC TILE RESISTANCE TO CHEMICALS:

Chemical	2 hours	24 hours
Lye 10%	No effect	weak effect
Soda 10%	No effect	weak effect
Hydrochloric acid 10%	No effect	weak effect
Citric acid 10%	No effect	No effect
Diesel oil	No effect	No effect
White spirit	No effect	weak effect
Acetic acid 30%	Weak effect	weak effect
Chromic acid	No effect	No effect
Acetone	No effect	No effect
Carbon Tetrachloride	No effect	severe effect
Ethanol	No effect	slight effect
Ethyl Ether	No effect	affected
Formaldehyde	No effect	No effect
Methanol	No effect	No effect
Ammonia	No effect	No effect
Ammonium Carbonate	No effect	No effect
Ferric Chloride	No effect	No effect
Sodium Carbonate	No effect	No effect
Glycerol	No effect	No effect
Hydrogen peroxide	No effect	No effect
Sodium Chlorite	No effect	No effect
Batadine	No effect	No effect
Glutar Aldehyde	No effect	No effect
Sterisol/Leiras	No effect	No effect

When installed MVT tile does not require any additional finish. After the factory applied finish has worn off apply a metalized acrylic finish (Taski/Lever brand). Please see Allstate maintenance sheet for complete maintenance program.