



“ALLSTATE RESILIENT FLOORING SINCE 1958”

www.allstaterubber.com
sales @allstaterubber.com

Allstate Rubber Flooring Adhesive #RT

Material Safety Data Sheet

FOR COATINGS, RESINS, AND RELATED MATERIALS

(Approved by U.S. Department of Labor “Essentially Similar” to Form OSHA-20).

HMIS III

H = 1

F = 0

PH = 0

DATE OF PREP: 06/17/2004

PREPARED BY: GREG WOOD

SECTION I

MANUFACTURED FOR: Stoler Industries (Allstate Rubber)

STREET ADDRESS: 2220 S. Hamilton St. Extension

CITY & STATE: Dalton, GA ZIP CODE: 30722

EMERGENCY TELEPHONE NO.:

CHEMTREC (24 hours) 800 424-9300

PRODUCT CLASS: Rubber Tile Adhesive

MANUFACTURER’S CODE IDENTIFICATION: RT Adhesive

SECTION II - HAZARDOUS INGREDIENTS

INGREDIENT NTP/IARC/ TLV LEL VAPOR PRESSURE

OSHA CARC PPM Mg/M

Ammonium hydroxide = 1.8% 50 >1

SECTION III - PHYSICAL DATA

BOILING RANGE: > 212 <F

VAPOR DENSITY : LIGHTER THAN AIR

EVAPORATION RATE: SLOWER THAN ETHER

PERCENT VOLATILE BY WEIGHT: 24-260%

WEIGHT PER GALLON: 9.8 – 10.2 lbs.

VOC EMISSION: 0 g/l (Calculated per CA. South Coast Rule 1168)

SECTION IV - FIRE & EXPLOSION HAZARD DATA

DOT CATEGORY: Nonflammable FLASH POINT: n/a

LEL: Not Known

EXTINGUISHING MEDIA: Water mist, dry chemical, CO₂, mechanical foam

UNUSUAL FIRE AND EXPLOSION HAZARDS: Liquid adhesive will not ignite. Dried adhesive will ignite if heated over 150°C and or/exposed to ignition source, producing CO, CO₂, smoke and hydrocarbons.

SPECIAL FIRE FIGHTING PROCEDURES: If dried adhesive ignites, use dry chemical, foam extinguishers, or a fog nozzle. For small fires, CO₂ extinguishers can be used. Use air mask when combating dried adhesive fires.

SECTION V - HEALTH HAZARD DATA

THRESHOLD LIMIT VALUE: None Established

EFFECTS OF OVEREXPOSURE: Wet-lightheadedness, nausea, mild dermatitis. Dry-None Acute-Eye, nose, throat irritation.

EMERGENCY AND FIRST AID PROCEDURES: Flush eyes with ample water. Wash skin with soap and water. If ingested, treat symptomatically and contact physician.

SECTION VI - REACTIVITY DATA

STABILITY: R Unstable P Stable

CONDITIONS TO AVOID: Closed area with open container.

HAZARDOUS DECOMPOSITION PRODUCTS: None

HAZARDOUS POLYMERIZATION: R May Occur P Will Not Occur

CONDITIONS TO AVOID: Strong acids or oxidants, temperatures below 35 <F

SECTION VII - SPILL OR LEAK PROCEDURES

STEPS TO BE TAKEN IN CASE OF MATERIAL IS RELEASED OR SPILLED: Scoop up excess with shovel, wash remainder with water.

WASTE DISPOSAL METHOD: Landfill or incinerate as per local and state regulations.

SECTION IX- SPECIAL PRECAUTIONS

PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING: Store in a cool, dry place. Optimum storage temperature 70EF.

OTHER PRECAUTIONS: Keep from freezing. Physical properties and performance may be altered if allowed to freeze. Keep sealed when not in use. Shelf life is one year in an unopened container.