



**Resistance to chemicals + Acids for Allstate Rubber tile + Stairtreads:**

<b>Agent</b>	<b>After 1 hour</b>	<b>After 24 hours</b>
Acetic acid 5%	<u>no change</u>	<u>no change</u>
Acetone	<u>no change</u>	<u>no change</u>
Ammonia 28%	<u>no change</u>	<u>no change</u>
Ammonium 10%	<u>no change</u>	<u>no change</u>
Ammonium hydroxide 28%	<u>no change</u>	<u>no change</u>
Amylacetate	<u>slight swelling</u>	<u>slight swelling</u>
Betadine 10%	<u>no change</u>	<u>no change</u>
Chloroform	<u>no change</u>	<u>no change</u>
Chromic acid 37%	<u>discoloration</u>	<u>discoloration</u>
Citric Acid 10%	<u>no change</u>	<u>no change</u>
Coffee/tea	<u>no change</u>	<u>slight swelling</u>
Ethyl alcohol 90 vol.	<u>no change</u>	<u>no change</u>
Ethylacetate	<u>Slight swelling</u>	<u>Slight swelling</u>
Hydrochloric acid 3%	<u>no change</u>	<u>no change</u>
Hydrogen Peroxide 3%	<u>no change</u>	<u>no change</u>
Iodine solution 2%	<u>discoloration</u>	<u>discoloration</u>
Lactic acid 90%	<u>no change</u>	<u>no change</u>
MEK	<u>slight swelling</u>	<u>slight swelling</u>
Methyl blue 0.1%	<u>no change</u>	<u>slight discoloration</u>
Nitric acid 10%	<u>no change</u>	<u>no change</u>
Nitric acid 30%	<u>slight yellowing</u>	<u>slight yellowing</u>
Phenol, watery	<u>no change</u>	<u>no change</u>
Silver nitrate 2%	<u>discoloration</u>	<u>discoloration</u>
Soda Lye 50%	<u>no change</u>	<u>no change</u>
Sodium carbonate 20%	<u>no change</u>	<u>no change</u>
Sodium hydroxide 10%	<u>no change</u>	<u>no change</u>
Sodium hypochloride 10%	<u>no change</u>	<u>brightening</u>
Sulfuric acid 3%	<u>no change</u>	<u>no change</u>

Sulfuric acid 30%	<u>slight swelling</u>	<u>slight swelling</u>
Trichloroethane	<u>slight swelling</u>	<u>slight swelling</u>

Please note, Local conditions and different brands of chemicals may react differently. We recommended that users conduct their own tests for a particular application.