

Mapei Spain, S.A.

C.I.F.A-80125495

www.mapei.es

C/ Valencia nº 11 Pol. Ind Can Oller

08130 Sta. Perpètua de Mogoda (BARCELONA)

Tel.: +34 93 343 50 50 - Fax: +34 93 302 42 29

CONSULT REPORT

CLIENT:**DESENVOLUPAMENTS TEXTIL CAROL, S.L.****APPLICATION:****Application of CORKTEX tiles on floor in Removable and Permanent installation based on the RdP done on March 22, 2015.**

After a request for consult by the applicator, a few small guidelines on the placements are written, but it is emphasized that it is very important to read the Technical Data Sheets of the products for the commented applications:

REMOVABLE INSTALLATION WITH ULTRABOND ECO FIX:

- **Support preparation:** the support must be uniformly dry, absorbent, flat, mechanically resistant, free of dust, friable parts, cracks, varnishes, waxes, oils, rust, remains of plaster or everything that can affect adhesion. If the support is cementitious, the moisture content should be a maximum of 2,5 to 3% and there should be no moisture lift.
- **Product preparation:** before starting the installation the floor, the adhesive and the bottom must be acclimatized at an application temperature between 15 and 35 °C.
- **Application:** it will be applied with serrated trowel of nº1 with a maximum consumption of 0,15 to 0,2 Kg/m². It is **essential to wait** for the complete evaporation of the water a waiting time that can vary between 30 min. to 12 hours, depending on temperature and quantity applied. The floor should not be laid before that time or when the product changes from paste color to transparent. Place the floor at that time and rub evenly.

PERMANENT INSTALLATION WITH ULTRABOND ECO V4 SP:

- **Support preparation:** the support must be uniformly dry, absorbent, flat, mechanically resistant, free of dust, friable parts, cracks, varnishes, waxes, oils, rust, remains of plaster or everything that can affect adhesion. If the support is cementitious, the moisture content should be a maximum of 2,5 to 3% and there should be no moisture lift.
- **Product preparation:** before starting the installation the floor, the adhesive and the bottom must be acclimatized at an application temperature between 15 and 35 °C.
- **Application:** mix the adhesive well in the drum before use. It will be applied with serrated trowel nº1 or 2 depending on the support to ensure that the adhesive is homogeneous and evenly distributed, with a maximum consumption of 0,25 to 0,4 Kg/m². It is **essential to wait** for a waiting time that can vary between 10 and 20 min. at 23 °C, or until the ULTRABOND ECO V4 SP has reached the proper viscosity and developed an enough tack to maintain contact with the support. In little or non-absorbent supports you must wait longer, but without exhausting the life of the product, which is about 40-45 minutes at 23 °C. The tiles would be applied by carefully massaging with a wooden trowel or roller as soon as it was placed and from the center to the ends to allow a complete humidification and eliminate air bubbles. The paving will be passable with caution at 3-5 hours and complete at 48-72 hours.

Consult the technical data sheets for the application, the marked conditions do not exempt from compliance with the rest contained in them.

To know in more detail the characteristics and the way of using the referred products, consult the corresponding technical data sheets available on the internet at the address www.mapei.com.

IMPORTANT NOTE: this report is issued by the technical services department regarding the generic use of the referenced products and in no case assumes any responsibility for the corresponding execution of the work.

Santa Perpètua de Mogoda, February 29, 2020.

Sincerely,
MAPEI SPAIN, S.A.



Agustín Villa Isorna
Technical Services Departament.